


# TECHNICAL DATA SHEET

## GENERAL INFORMATION

- Name : Panax Yellow 750A
- Chemical Type : The mixture of PY-83 and yellow pigments & extenders
- Main Application : Paints, Ink, Water Base
- Pigment No. : Not listed

## COLOR SHADE

Full Shade



Tinting Shade (1:25)



## DESCRIPTIONS

Non-toxic pigment, Good Light Fastness, Good Heat Resistance

## PHYSICAL PROPERTIES

- Specific Gravity : 1.5
- Moisture Content : Max 2.0 %
- PH(Kneader extract) : 6-8
- Dispersion( $\mu\text{m}$ ) : Max 60 (Aprecision gage) by Hoover Muller (50\*2)
- Hardness : Slightly Hard

## RESISTANCE DATA

- Light Fastness (Full Shade) : 6 (1-8)
- Light (Tint Shade) : 5 (1-8)
- Heat (210°C×10min) : 3 (1-5)



## UKSEUNG CHEMICAL CO., LTD

HEAD OFFICE : # 174, Gaejwa-ro, Geumjeong-gu, Busan, South Korea  
TEL. 051) 718-5345 ~ 8 / FAX 051) 529-7272