

TECHNICAL DATA SHEET

GENERAL INFORMATION

- Name : Panax ECO Yellow 80W
- Chemical Type : The mixture of PY-83 and yellow pigments & extenders
- Main Application : Paints, Plastics
- Pigment No. : Not listed

COLOR SHADE

Full Shade



Tinting Shade (1:25)



DESCRIPTION

Non-toxic Pigment

PHYSICAL PROPERTIES

- Specific Gravity : 3~3.5g/cm³
- Bulking Value(cm³/100g) : 325
- Moisture Content : Max 2.0 %
- pH : 6~8
- Oil Absorption(cc/100g) : 24~28(cc/100g)

RESISTANCE DATA

- Light Fastness (Full Shade) : 3 (1-5)
- Light Fastness (Tint Shade) : 3 (1-5)
- Heat (210°C×10min) : 3 (1-5)
- Heat (150°C×10min) : 3 (1~5)
- 5% HCl : 4
- 5% NaOH : 4
- Water : 5
- Ethanol : 4
- Xylene : 4
- MEK : 3

UKSEUNG CHEMICAL CO., LTD



HEAD OFFICE : # 174, Gaejwa-ro, Geumjeong-gu, Busan, South Korea
TEL. 051) 718-5345 ~ 8 / FAX 051) 529-7272