

# TECHNICAL DATA SHEET

## GENERAL INFORMATION

- Name : Panax Orange 900S
- Chemical Type : PO-34
- Main Application : Paints, Plastics
- Pigment No. : Pigment Orange 34

## COLOR SHADE

Full Shade



Tinting Shade (1:25)



## DESCRIPTION

Non-toxic pigment

## PHYSICAL PROPERTIES

- Specific Gravity : 1.4
- Moisture Content : Max 2.0 %
- pH(Kneader extract) : 6-8
- Dispersion( $\mu\text{m}$ ) : Max 50 (Aprecision gage) by Hoover Muller (50\*2)
- Hardness : Soft

## RESISTANCE DATA

- Light Fastness (Full Shade) : 6~7 (1-8)
- Light (Tint Shade) : 4~5 (1-8)
- Heat (210°C×10min) : 4 (1-5)



## UKSEUNG CHEMICAL CO., LTD

HEAD OFFICE : # 174, Gaejwa-ro, Geumjeong-gu, Busan, South Korea  
TEL. 051) 718-5345 ~ 8 / FAX. 051) 529-7272