

**PANAX YELLOW 990GR**
**PRODUCT DESCRIPTION**

Color Index	Pigment Yellow 34
C.I. No.	77603
Chemical Type	Lead Chromate
CAS No.	1344-37-2
EU No.	215-693-7

**PHYSICAL DATA**



Appearance	Yellow Powder	
pH (2% aqueous)	5 ~ 7	ISO 787-9
Specific gravity	5.4 g/cm <sup>3</sup>	ISO 787-10
Bulk volume	140cm <sup>3</sup> /100g	ISO 787-11
Oil absorption	18 g/100 g	ISO 787-5

**FASTNESS PROPERTIES**

Acid	4	DIN EN ISO 20105-A03
Alkali	2	DIN EN ISO 20105-A03
Water	5	ISO 2836
Ethanol	5	ISO 2836
Xylene	5	ISO 2836
MEK	5	ISO 2836
DOP	5	ISO 2836
Heat / 150°C, 10 min	5	ISO 787-21
Heat/ 210°C, 10 min	4	ISO 787-21
Light 1/3 SD	5	ISO 105-B01
Light 1/25 SD	4	ISO 105-B01
Bleeding	5	

**STANDARD PACKAGING**

Paper bags	25 kg
Big Bags type C	On request

**FULL SHADE REDUCTION 1:25 TiO<sub>2</sub>**

**CHEMICAL STRUCTURE OF THE PIGMENT**

**APPLICATION RECOMMENDATION**

Oil Ink	
Solvent Ink	
Water Flexo Ink	
Paint (Oil Base)	recommended
Paint (Water Base)	
Plastics	
Textile	
Artist Color	

**REMARKS**

Non-Coating type

Our product specific end application information are based upon our current knowledge. They are presented without any representation or warranty concerning the suitability, performance or correctness of the product for a particular application or use. Significant variations can occur between test results and results obtained in actual use. We strongly advise that the customer test the product in the specific intended application under conditions expected during use.

**HEAD-OFFICE**

#174, GAEJWA-RO, GEUMJEONG-GU,  
 BUSAN, KOREA / 609-845  
 Tel.: +82 51 5231515~8  
 Fax: +82 51 5296326  
 Email: trade@ukseung.co.kr  
<http://www.ukseung.co.kr>

**EUROPE OFFICE**

UK SEUNG Europe GmbH Kirchrainstr. 7  
 D-63762 Grossostheim, Germany  
 Tel. : +49 6026 9997875  
 Fax: +49 6026 9997881  
 Email: info@ukseung-europe.de  
<http://www.ukseung-europe.de>